

**OBEIKAN TECHNICAL FABRICS CO. LTD.**

PO Box 1087, Riyadh 11431 Kingdom of Saudi Arabia

Tel: +966 1 2653533 Fax: +966 1 2653438

Website: www.obeflex.comEmail: otf@obeikan.com.sa**TECHNICAL DATA SHEET****Product: BLOCKOUT 850 (GLOSS), FR****Application:**

- Event tents, Work tents, Medical tents..
- Shelters

PROPERTIES	TEST METHOD	METRIC	ENGLISH
Support Cloth	(DIN 60001)	Polyester	Polyester
Ends/Picks	(DIN EN 1049-2)	8 x 9 per cm	20/23 per inch
Yarn (dtex)	(DIN EN ISO 2060)	1100	
Weave	(DIN ISO 9354)	1/1 plain	1/1 plain
Greycloth-weight	(DIN EN ISO 2286-2)	200 g/m2	5.9 oz./sq.yd.
Base Coat		PVC	PVC
Top Coat		Acrylic	Acrylic
Total weight	(DIN EN ISO 2286-2)	850 ±20 g/m2	24.87 oz./sq.yd.
Tensile Strength	(DIN 53354)	3000/2500 N/5cm	342/285 lbs/inch
Tear Resistance	(DIN 53356)	300/250 N	68/57 lbs
Extreme Working Temperature		-30oC/+70°C	-22oF/+51°F

Features:

- ☞ UV and fungus resistant
- ☞ High-frequency and hot-air weldable
- ☞ Acrylic and PVDF lacquer available
- ☞ Excellent weatherability and durability
- ☞ Super opaque material
- ☞ Lacquered on both sides

NOTE: Information listed above is based on our general experience and observation and is given in good faith. OTF will not accept any

Issue date: 21st May 2008

