



PRODUCT DATA SHEET- Coated Fabrics

Code: PXX200-A59

DESCRIPTION	:	BOTH SIDE PVC COATED POLYESTER FABRIC	Ref. No: TS/CF-NPD/PDS/136
Base Fabric	:	Made out of High Tenacity Polyester Filament Yarn	Rev. No.00
Coating Material	:	Non Foam PVC	Date:24/12/13
Finish	:	GLOSSY	
Yarn	High Tenacity Polyester		
Denier	Warp/Weft	1000/1300	
Construction	Warp/Weft	21 EPIX22 PPI	
Weave	Plain		
Greige fabric GSM	215		

Coated Fabric

Parameter		Unit	Specification	Test method
Weight/m ²		g	630 ± 5%	IS 7016 (Part I)-1982
Thickness		mm	0.45 Minimum	IS 7016 (Part I)-1982
Breaking Strength	Warp	Kg / 5 cm	250 Minimum	IS 7016 (Part II)-1981
	Weft		250 Minimum	
Tear Strength (Sample size 200mm x 150mm with 50mm tongue)	Warp	kg	40 Minimum	BS: 3424 Part 5 Method 7A
	Weft		40 Minimum	
Adhesion of PVC to base fabric	Warp	kg / 5.0cm	7.0 Minimum	IS 7016 (Part V)-1987
Water Proofness @ 220 psi		---	No leak	IS:7016 (Part 7)-1986

Our coated fabrics are available in wide range of colors and as well as double side or single side coated as desired by customers. SRF also offers specialty fabrics with high UV stability, flame retardance with acrylic and PVDF finishes.

Disclaimer: The information contained herein, or that supplied by us, or on our behalf in any manner, is based on data obtained by our own research and is considered accurate. We are submitting it to you to assist you in your endeavors. This information is subjected to revision as additional technology is developed. SRF Ltd., assumes no liability or obligation for damages incurred through the use of this information and makes no warranty or representation regarding the use of this information.